

DICRISTAL 75 PLUS

Technical sheet

Recommended use : Flexible windows

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Thickness	0.75		mm	ISO 5084
Coating	PVC			
Finish	Transparent Anti UV			
Weight	915		g/m ²	ISO 3801
Light transmission	92		%	
Width	140		cm	
Roll length	30		ml	

Fabric resistance

Flexibility	46		PHR	
Tensile strength	25.4	22.1	N/mm ²	ASTM D 882-02
Elongation at break	300	310	%	ASTM D 882
Dimensional stability	2		%	10 min / 50°
Dimensional stability	4.5		%	ASTM D 1204-02 (10 min / 80°)
Weather resistance	PASS			ASTM D1499 (Xenotest: 2000 hours)
Cold resistance	-20		°C	ASTM D 1790



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

