

# DICRISTAL FR 50

## Technical sheet

Recommended use : Flexible windows

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Thickness	0.5		mm	ISO 5084
Coating	PVC			
Finish	Transparent Anti UV			
Weight	650		g/m <sup>2</sup>	ISO 3801
Width	137		cm	
Roll length	50		ml	

## Fabric resistance

Tensile strength	26	24	MPa	ISO 527-3/2/200
	240	260	%	ISO 527-3/2/200
Dimensional stability	-4		%	DIN 53377
Cold resistance	-10		°C	NF EN 1876-2
Warm resistance	50		°C	[24h]
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837



RESOURCE



## SAINT CLAIR TEXTILES

415, avenue de Savoie

F-38110

Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

